

**RAMPF®****ESTERLÖSSL GMBH**  
COMPOSITE-TECHNOLOGIE + WERKSTOFFE

<b>Blockmaterial</b> <b>RAKU- TOOL®</b>	Anwendung	Dichte (g/cm <sup>3</sup> )	Wärmeform- beständigkeit ISO 75 (°)	Wärme- ausdehnungs- koeffizient	Druckfestigkeit ISO 604 (Mpa)	Dimension (mm)
<b>MB 0540</b>	Modell/ DKM	0,6	60 -65	45 - 50	15	1500 x 500 x 50 1500 x 500 x 75 1500 x 500 x 100 1500 x 500 x 150
<b>MB 0600</b>		0,7	70 -75	50 - 55	20	1500 x 500 x 25 1500 x 500 x 50 1500 x 500 x 75 1500 x 500 x 100 1500 x 500 x 150 1500 x 500 x 200
<b>MB 0670</b>		0,7	75 -80	50 - 55	20	1500 x 500 x 25 1500 x 500 x 50 1500 x 500 x 75 1500 x 500 x 100 1500 x 500 x 150 1500 x 500 x 200
<b>MB 0720</b>		0,7	75 - 80	50 - 55	25	1500 x 500 x 25 1500 x 500 x 50 1500 x 500 x 75 1500 x 500 x 100 1500 x 500 x 150 1500 x 500 x 200
<b>WB 0801</b>	Formen Tiefzieh- werkzeuge Gießereimodelle	0,8	85 - 90	45 - 50	45	1500 x 500 x 50 1500 x 500 x 75 1500 x 500 x 100 1500 x 500 x 150 1500 x 500 x 200

